

ALT Primer 276 Resin



Product Data Sheet

Description

ALT Primer 276 Resin is a high performance thixotropic PMMA two-component, rapid-curing, resin primer.

Applications

ALT Primer 276 Resin is a rigid primer used as a primer/sealer for concrete, masonry, wood, and other substrates. ALT Primer 276 promotes adhesion and is in conjunction with ALT roofing, waterproofing and traffic surfacing systems.

Packaging

ALT Primer 276 is supplied in 10-kg re-sealable drums with locking rings.

Coverage Rate (approximate)

Smooth substrates: 0.037 kg/sf (0.40 kg/m²)
 Fine grained substrates: 0.046 kg/sf (0.50 kg/m²)
 Rough substrates: 0.074 kg/sf (0.80 kg/m²)

Gross yield/10-kg unit: 269 ft² (25 m²) @ 0.4 kg/m²

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

Storage

Always store in cool and dry location. Do not store in direct sunlight or in temperatures below 32°F(0°C) or above 77°F(25°C). Approximate shelf life is 12-months when left sealed, unmixed and with proper storage.

Application Conditions

The product can be applied at substrate and ambient temperatures between 35°F (1.7°C) and 95°F (35°C).

Note: The clean and fully cured primer can be coated after a minimum of approximately 30-45 minutes up to a maximum of 6-months. If the surface of the primer becomes dirty or contaminated or left exposed to the elements for more than 12-hours, thoroughly clean the in-place and cured primer with ALT Activator. ALT Activator should be allowed a minimum of 20-minutes evaporation time after application, and over-coated within 60-minutes of application.

Mixing & Catalyzing

Thoroughly mix the entire drum of resin for 2-3 minutes before each use, and prior to pouring off resin into a second container if batch mixing. Catalyze only

the amount of material that can be used within 10-15 minutes. Add pre-measured catalyst to the resin component, stir for 2-minutes using a slow-speed mechanical agitator or stirring stick and apply to substrate. The amount of catalyst added is based on the weight of the resin used.

catalyst required per 1-kg of resin used					
6% Catalyst 35°F to 41°F (1.7°C to 5°C)		4% Catalyst 41°F to 77°F (5°C to 25°C)		2% Catalyst 77°F to 95°F (25°C to 35°C)	
g	kg	g	kg	g	kg
60	.06	40	.04	20	.02

Working Times (at 68°F (20°C))

- Pot Life: approx. 10 to 15-minutes
- Rainproof: approx. 30-minutes
- Next Coat: approx. 30 to 45-minutes
- Fully Cured: approx. 2 to 3-hours

The times noted above are approximate, provided as a guideline, and may vary. Actual set times and cure should be established in the field based on actual field conditions.

Tool Cleaning

When work is interrupted or completed, tools must be thoroughly cleaned with ALT Activator before the resin hardens.

Safety Recommendations

Refer to product Material Safety Data Sheet (MSDS) prior to use or handling.

Disposal

Catalyzed and cured resin may be disposed of in standard landfills. Uncured resin is considered a hazardous material and must be handled as such, in accordance with local, state and federal regulations.

Ordering Information

- ALT Primer 276 Resin (clear)**
- Item #: 113-000-005U 10-kg can
- ALT Primer 276 Resin (white)**
- Item #: 113-910-005U 10-kg can

Application Guidelines

Handling

Keep away from open fire, flame or any ignition source. Vapors may form explosive mixture with air. Avoid skin and eye contact with this material. Avoid breathing fumes. Do not eat, drink or smoke in area of application. Refer to product Material Safety Data Sheet (MSDS) for additional information pertaining to this product and prior to use or handling.

Personal Protection Equipment

Workers should wear appropriate clothing to protect from accidental skin contact. When mixing or applying this product workers must use butyl rubber or nitrile gloves. Safety glasses with side shields are required for eye protection.

In enclosed spaces, use local exhaust ventilation to maintain worker exposure below TLV. If the airborne concentration poses a health hazard, become irritating or exceeds recommended limits, use a NIOSH approved respirator in accordance with OSHA Respirator Protection requirements under 29 CFR 1910.134. The specific type of respirator will depend on the airborne concentrations. A filtering face piece or dusk mask is not acceptable for use with this product if TLV filtering levels have been exceeded.

Surface Preparation

All substrates must be clean, dry, free of oil, grease, curing compounds, release agents, laitance, gross irregularities, loose, unsound or foreign material such as moss, algae growth, dirt, ice, snow, water or any other condition that would be detrimental to adhesion of resin to the substrate. Apply ALT primer to substrate as required. Refer to ALT "Substrate Preparation & Priming Guidelines" for specific recommendations and requirements. Contact ALT Technical Department for recommendations regarding specific applications.

Application

After mixing, apply resin to clean and prepared substrate at the required consumption using ALT approved rollers or brushes. The resin should be spread evenly onto the surface. See individual system specifications for specific guidelines regarding application of primer, membrane, topcoat and/or surfacing.

Remarks/Comments

The information provided regarding application of ALT Global products is based on extensive development work, as well as many years of experience, and is given to the best of our knowledge. However, due to the diverse conditions encountered in building construction, it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make alterations in keeping with technical developments or improvements.

DISCLAIMER

NO WARRANTY, EXPRESS OR IMPLIED, IS MADE IN THIS DOCUMENT. THE PRODUCT IS NOT CLAIMED TO BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE. User and certified ALT Global system applicators determine suitability only. See individual ALT Global System product data sheets, MSDS sheets, guide specifications and details for complete information regarding the suitability, application and handling of ALT Global products.