

ALT S223 Filler



Product Data Sheet

Description

ALT S223 Filler is a proprietary high performance blended filler component.

Applications

ALT S223 Filler powder is mixed with ALT R210 Resin to create ALT RS233 Mortar, a trowel-able mortar used in approved ALT deck coating, surfacing and waterproofing systems.

Color

ALT S223 Filler is supplied in a grey/beige base.

Packaging

ALT S223 Filler is supplied in 23-kg bags.

Coverage Rate

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

Storage

Always store in cool and dry location. Do not store in direct sunlight or in temperatures below 32°F(0°C) or above 77°F(25°C). Approximate shelf life is 6-months when left sealed, unmixed and with proper storage.

Application Conditions

The product can be applied at substrate and ambient temperatures between 37°F (3°C) and 95°F (35°C).

Mixing & Catalyzing

Thoroughly mix the entire drum of ALT R230 Resin for 2-3 minutes before mixing with ALT S223 Filler. Transfer the R230 resin component to a clean, dry container large enough to accommodate the combined resin and filler components with room for mixing. Using a slow-speed mechanical agitator, slowly add the entire bag of S223 Filler to the R210 resin component while stirring; continue mixing for 2 to 5-minutes or until achieving a smooth lump-free mortar consistency. The mixing ratio is 1 to 2.3 resin to filler respectively. Catalyze only the amount of material that can be placed within 10-15 minutes. The added ALT Catalyst should be based ONLY on the weight of the resin used, and not the entire batch (resin + filler) weight. Thoroughly mix catalyst into resin-mortar for 1-minute, change material into second clean and dry bucket, and thoroughly mix resin-mortar for 1-minute

additional. Remix un-catalyzed resin-mortar before each use, and prior to pouring off into a second container if batch mixing.

ALT Catalyst required per 1-kg of resin used

6% Catalyst 37°F to 41°F (3°C to 5°C)		4% Catalyst 41°F to 59°F (5°C to 15°C)		2% Catalyst 59°F to 95°F (15°C to 35°C)	
g	kg	g	kg	g	kg
60	.06	40	.04	20	.02

Working Times (at 68°F (20°C))

- Pot Life: approx. 15-minutes
- Rainproof: approx. 30-minutes
- Next Coat: approx. 1-hour
- Fully Cured: approx. 3-hours

The times noted above are approximate, provided as a guideline, and may vary. Actual set times and cure should be established in the field based on actual field conditions.

Tool Cleaning

When work is interrupted or completed, tools must be thoroughly cleaned with ALT Activator before the resin hardens.

Safety Recommendations

Refer to product Material Safety Data Sheet (MSDS) prior to use or handling.

Disposal

Product may be swept up and discarded. When combined with ALT R210 Resin, catalyzed and cured resin-mortar may be disposed of in standard landfills. Uncured resin-mortar is considered a hazardous material and must be handled as such, in accordance with local, state and federal regulations.

Ordering Information

ALT S223 Filler
#118-000U 23.0 kg bag

Application Guidelines

Handling

Keep away from open fire, flame or any ignition source. Vapors may form explosive mixture with air. Avoid skin and eye contact with this material. Avoid breathing fumes. Do not eat, drink or smoke in area of application. Refer to product Material Safety Data Sheet (MSDS) for additional information pertaining to this product and prior to use or handling.

Personal Protection Equipment

Workers should wear appropriate clothing to protect from accidental skin contact. When mixing or applying this product workers must use butyl rubber or nitrile gloves. Safety glasses with side shields are required for eye protection.

In enclosed spaces, use local exhaust ventilation to maintain worker exposure below TLV. If the airborne concentration poses a health hazard, become irritating or exceeds recommended limits, use a NIOSH approved respirator in accordance with OSHA Respirator Protection requirements under 29 CFR 1910.134. The specific type of respirator will depend on the airborne concentrations. A filtering face piece or dusk mask is not acceptable for use with this product if TLV filtering levels have been exceeded.

Surface Preparation

All substrates must be clean, dry, free of oil, grease, curing compounds, release agents, laitance, gross irregularities, loose, unsound or foreign material such as moss, algae growth, dirt, ice, snow, water or any other condition that would be detrimental to adhesion of resin to the substrate. Apply ALT Primer to substrate as required. Refer to ALT "Substrate Preparation & Priming Guidelines" for additional information and requirements. Contact ALT Global Technical Department for recommendations regarding specific applications.

Application

Tape out the area of work in a checkerboard fashion using duct tape or fiber reinforced masking tape. After mixing, apply ALT RS233 Mortar to clean, prepared and primed substrate at the required consumption using a trowel. The resin-mortar should be spread evenly onto the surface at a uniform depth. Smooth and even-out resin-mortar immediately by rolling with an ALT approved spiked roller. Before resin begins to cure, remove all masking tape. See individual system specifications for specific guidelines regarding application of additional topcoats.

Remarks/Comments

The information provided regarding application of ALT Global products is based on extensive development work, as well as many years of experience, and is given to the best of our knowledge. However, due to the diverse conditions encountered in building construction, it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make alterations in keeping with technical developments or improvements.

DISCLAIMER

NO WARRANTY, EXPRESS OR IMPLIED, IS MADE IN THIS DOCUMENT. THE PRODUCT IS NOT CLAIMED TO BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE. User and certified ALT Global system applicators determine suitability only. See individual ALT Global System product data sheets, MSDS sheets, guide specifications and details for complete information regarding the suitability, application and handling of ALT Global System products.